

#### COMPANY TECHNICAL SPECIFICATION

CTS 3 - 73

# POLYPROPYLENE BUPLENE® HOMOPOLYMER WITH IMPROVED FLOWABILITY 6131 and 6231

This specification is applicable only for products intended for export.

**Product Polypropylene Buplene®** is specified for nutrient products contact.

#### 1. Technical requirements and test methods

30	Properties	Unit	Values of grades		TD 4 M 41 1
№			6131	6231	Test Method
1.	Melt flow rate at 230 °C, loading 2,16 kg, min - max	g/10min	25 - 30	16 - 25	ASTM D 1238 EN ISO 1133
2.	Density at 23 °C, min - max	kg/m <sup>3</sup>	899 - 906	899 - 906	ASTM D 792
3.	Deflection temperature under Flexural load at 1,82 MPa, min	<sup>0</sup> C	50	50	ASTM D 648 EN ISO 75-2
4.	Tensile strength at yield, at 50 mm/min, min	MPa	29	29	ASTM D 638 EN ISO 527-1
5.	Bending modulus 1% secant, min	MPa	1100	1100	ASTM D 790

Note: Preparation of the samples for the physical mechanical test-through injection moulding as per ASTM D 4101.

### 2. Product description

The polypropylene is granulated, stabilized normally and in natural appearance.

It is used for textile and paper impregnation and production of monofilaments at high processing rate.

# 3. Method for production and sampling

- 3.1 It is produced by molecular mass extrusion regulation so called CR-T process.
- 3.2 Sampling procedure complies with ISO 8213.

## 4. Packages, marking and storage

- 4.1 Polyethylene bags, each with a mass of the material 25 kg.
- 4.2 Every package is marked with product code, batch and date of production.
- 4.3 It stored in covered, dry and clean warehouses at distance not less than 1 m away from heating appliances.

## 5. Transportation and documents

- 5.1 Covered and clean vehicles, protected from moisturizing, mechanical damages and pollution.
- 5.2 Each batch shall be accompanied by production specification of test results according to point 1.
- 5.3 Product SDS (Safety Data Sheet) is submitted to the user prior or at the time of first delivery.

end

Revision 03	Validity by: 01.01.2016	Page 1 of 1